

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



10/524490



(43) International Publication Date  
11 March 2004 (11.03.2004)

PCT

(10) International Publication Number  
WO 2004/020731 A1

(51) International Patent Classification<sup>7</sup>: D06P 3/00, 1/00

(21) International Application Number:

PCT/EP2003/009097

(22) International Filing Date: 16 August 2003 (16.08.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

102 38 890.3

24 August 2002 (24.08.2002)

DE

(71) Applicant (for all designated States except US): DYSTAR  
TEXTILFARBEN GMBH & CO. DEUTSCHLAND  
KG [DE/DE]; Industriepark Höchst, Gebäude B 598,  
65926 Frankfurt am Main (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): KRABBE, Guido  
[DE/DE]; Feldbergstrasse 41, 65817 Eppstein-Ehlhalten  
(DE). MACH, Hort-Roland [DE/DE]; Am Pfingstborn  
25, 61479 Glashütten (DE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,  
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,  
VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: TEXTILE SPUN-DYED FIBER MATERIAL AN USE THEREOF FOR PRODUCING CAMOUFLAGE ARTICLES

(57) Abstract: The present invention relates to textile fiber material comprising spun-dyed aramid fibers or mixtures of spun-dyed aramid fibers and undyed cellulosic fibers for producing military camouflage articles, wherein the aramid fiber fraction is spun-dyed with a colorant having a chlorophyll-like reflectance in the IR region, and to its use for producing military camouflage print articles.



WO 2004/020731 A1

**THIS PAGE BLANK (USPTO)**

10/524490

DT01 Rec'd PCT/PTO 14 FEB 2005

## Description

5

Textile spun-dyed fiber material and use thereof for producing camouflage articles

10

The present invention relates to textile fiber material comprising spun-dyed aromatic polyamide fibers (aramid fibers) or mixtures of spun-dyed aramid fibers with undyed cellulosic fibers and to its use for producing camouflage articles.

15

Textiles for military applications, especially uniforms and combat suits, are required by various military authorities to be low flammable or flame retardant. At the same time, properties such as colorfastnesses, IR reflectance characteristics, camouflaging effect due to patterning/coloration and wear properties shall not be inferior to what is achievable with hitherto customary textile materials.

20

For low-flammable textiles the obvious choice is aramid fibers. However, conventional printing and dyeing processes do not provide products having adequate colorfastnesses. Similarly, the stipulated infrared reflectance performance (chlorophyll-like reflectance curve) cannot be achieved.

25

It is an object of the present invention to provide a process for producing camouflage articles based on aramid fibers or based on mixtures of aramid fibers and cellulosic fibers which provides the abovementioned performance profile stipulated by military authorities.

30

EP 1 111 124 A1 discloses a process for producing textile camouflage articles which comprises a spun-dyed fiber material composed of synthetic fibers or of a mixture of synthetic fiber and cellulosic fiber being printed with camouflage patterns. In the spun-dyed textile material, even in the case where it is a fiber blend, only the synthetic fiber fraction is spun-dyed with a dye having a chlorophyll-like reflectance in the IR region. Only the cellulosic fiber portion is then dyed in the second step. The synthetic fibers specified in this cited document are in particular polyester fibers and

(aliphatic) polyamide fibers.

It has now been found that, surprisingly, textiles based on aramid fibers or based on mixtures of aramid fibers and cellulosic fibers can be respectively dyed and printed in similar manner to that indicated in EP 1 111 124 A1. This was unforeseeable because the colorants used for prior art spin dyeing do not withstand the requirements needed for spinning aramid, such as thermal requirements or solvent resistance.

Accordingly, military requirements can be met by having a fiber material in which the fraction of aramid fibers has been spun dyed with a certain colorant which has the required IR reflectance characteristics subsequently cross-printed or -dyed, although in the case of cellulosic blend substrates it is only the cellulose fraction which is printed or dyed in this second step.

This process has the additional advantage that it is no longer necessary to use two dye classes and distinct fixing operations when printing or dyeing blend fabrics, since the aramid fiber fraction has already been covered by the spin dyeing, which also already comprises the desired chlorophyll-like IR reflectance.

The present invention thus provides a textile fiber material comprising spun-dyed aramid fibers or mixtures of spun-dyed aramid fibers and undyed cellulosic fibers for producing military camouflage articles, wherein the aramid fiber fraction is spun-dyed with a colorant having a chlorophyll-like reflectance in the IR region.

The present invention also provides for the use of textile fiber material comprising spun-dyed aramid fibers for producing military camouflage print articles, which comprises camouflage patterns being printed on in a conventional manner.

The present invention further provides for the use of textile fiber material comprising mixtures of spun-dyed aramid fibers and undyed cellulosic fibers for producing military camouflage articles, which comprises the cellulose fraction being dyed or camouflage printed.

The textile fiber materials of the present invention are in particular wovens or formed-loop knits and can consist of aramid fibers only. But preferably they consist of mixtures of aramid fibers with cellulose. Particular preference is given to mixtures of aramid fibers and low-flammability regenerated cellulose fibers, such as for example Lenzing AG's commercial product Lenzing FR.

With regard to the end use, the aramid fiber fraction of the textile fiber materials according to the present invention is generally spun dyed in a medium gray, green, brown or olive shade. Useful colorants, i.e. dyes and pigment preparations, include all colorants which are suitable for spin dyeing, which meet the requirements for the spin dyeing of aramid fibers and which have the necessary chlorophyll-like reflectance in the IR region.

These colorants can be used alone or mixed with each other. To obtain the desired basic hues, they can further be combined with further colorants useful in spin dyeing. However, care must always be taken to ensure that the IR reflectance characteristics of the end product do not have a disruptive or adverse effect on the chlorophyll-typical curve. Provided this prerequisite is met, the mixing ratios of the individual colorants used are not critical and are only determined by the desired basic hue.

Preferred colorants useful for spin dyeing the aramid fiber fraction include for example C.I. Vat Blue 05, C.I. Vat Blue 64, C.I. Vat Blue 66, C.I. Pigment Blue 15, C.I. Pigment Blue 15.1, C.I. Pigment Blue 15.3, C.I. Pigment Blue 28, C.I. Pigment Green 7, C.I. Pigment Green 17, C.I. Pigment Green 36, C.I. Pigment Green 50, C.I. Pigment Black 7, C.I. Pigment Black 11, C.I. Pigment Black 32, C.I. Pigment Yellow 42, C.I. Pigment Yellow 53, C.I. Pigment Yellow 83, C.I. Pigment Yellow 110, C.I. Pigment Yellow 138, C.I. Pigment Yellow 139, C.I. Pigment Yellow 164, C.I. Pigment Yellow 183, C.I. Pigment Yellow 184, C.I. Pigment Brown 24, C.I. Pigment Brown 29, C.I. Pigment Brown 31, C.I. Pigment White 6, C.I. Pigment Red 101, C.I. Pigment Red 144, C.I. Pigment Red 149, C.I. Pigment Red 178 and C.I. Pigment Red 179, which are all known and commercially available or preparable by methods known to one skilled in the art. Preference is also given to the commercial products Sicomix®

IR-Schwarz 00-6760 and Sicomix® Schwarz 00-8530 from BASF AG, and also Bayferrox Rot 600, Bayferrox Rot 655 and Bayferrox 960 from Bayer AG.

- 5 The spin dyeing process is known per se. In spin dyeing, the spinning solution or melt is admixed with pigment dyes or soluble dyes which remain in the fiber at the coagulation stage and thus color the fiber. The colorants are preferably added in the form of masterbatches which may already contain any assistants required. Details concerning spin dyeing may be found in Römpp Chemielexikon, 9th edition, 1992, 10 Volume 5, page 4247 and especially the references cited therein. Aramids suitable for producing aramid fibers are known and can be commercially acquired.

Textile fiber material according to the present invention that consists exclusively of spun-dyed aramid fibers is also useful as such for camouflage articles when a solid 15 color is acceptable. In this case, the desired hue is obtained exclusively by spin dyeing using appropriate amounts of colorant.

Generally, however, it is used for producing military camouflage print articles. To this end, the desired camouflage patterns are printed on in the corresponding camouflage hues in a second step. This step may employ the same colorants as 20 already used in spin dyeing, but advantageously customary textile print pigment preparations are used for this purpose. It is advantageous in this case to produce the spin dyeing in that shade which corresponds to the lightest hue of the camouflage print pattern and to print on the darker patterns. The lightest hue is generally light green, khaki or light olive.

25 When the textile fiber material of the present invention comprises a mixture of spun-dyed aramid fibers and undyed cellulosic fibers, it can be used for producing military camouflage articles by exclusively dyeing or printing the cellulose fraction in a second operation. If a single-colored end product is to be obtained, the spun-dyed 30 product is cross-dyed with a dye suitable for cellulosic fibers. It is advantageous here for the hue produced by the spin dyeing to be very close to the final hue.

Generally, however, the textile fiber materials of the present invention that comprise

a mixture of spun-dyed aramid fibers and undyed cellulosic fibers are printed with camouflage patterns in a second operation, again using dyes suitable for cellulose. It is preferable in this case for the spin dyeing to be executed in a medium gray, green, brown or olive hue and for the subsequent printing to be executed with typical camouflage print hues (according to the requirements of the respective army) such as black, brown and various olive or green shades. The medium shades of the spin-dyeing are blotted out by the deeper overprinted shades and do not adversely disrupt the overall appearance of the finished product.

Useful colorants for dyeing or printing the cellulose fraction include all colorants suitable for cellulose, although care must be taken to ensure that their IR reflectance curve is similar to that of chlorophyll or at least does not adversely affect the reflectance curve of the dye used in spin dyeing. Moreover, the colorants used have to meet the particular colorfastness requirements.

In one version of the present invention, however, it is also possible to print with an extremely low reflectance black dye which completely eliminates the chlorophyll-like reflectance curve. In this case, the IR reflectance values correspond for example to those of natural soil, so that their use for camouflaging purposes is advantageous here too. It is especially the combination of chlorophyll-like reflectance and low reflectance which was responsible for the camouflage effect.

The colorants useful for dyeing and printing the cellulose fraction can likewise be used alone or mixed with each other in wide mixing ratios.

Preferred dyes for cellulose are in particular vat dyes and sulfur dyes.

Particularly useful dyes are C.I. Vat Yellow 4, C.I. Vat Yellow 33, C.I. Vat Yellow 46, C.I. Vat Orange 1, C.I. Vat Orange 7, C.I. Vat Orange 11, C.I. Vat Orange 15, C.I. Vat Blue 5, C.I. Vat Blue 19, C.I. Vat Blue 66, C.I. Vat Green 1, C.I. Vat Green 3, C.I. Vat Green 9, C.I. Vat Green 13, C.I. Vat Brown 1, C.I. Vat Brown 3, C.I. Vat Brown 57, C.I. Vat Black 7, C.I. Vat Black 8, C.I. Vat Black 9, C.I. Vat Black 19, C.I. Vat Black 25, C.I. Vat Black 27, C.I. Vat Olive 27, C.I. Sulfur Black 1, C.I. Sulfur Black 6 and C.I. Sulfur Black 7.

The cellulose fraction of the textile spun-dyed fiber material of the present invention can be dyed and printed according to conventional methods for applying the various classes of dye, for example as described in H. Rath, Lehrbuch der Textilchemie, Springer Verlag, Berlin, Heidelberg, New York, 3rd edition 1972, especially pages 557-568, 571-575, 678-683 and 703-704 or in M. Peter and H.K. Rouette, Grundlagen der Textilveredlung, Deutscher Fachverlag, 13th revised edition, 1989, especially pages 500-509 and 624-625.

10 **Example 1:**

An aramid fiber spin dyeing masterbatch consisting of 5% of Vat Blue 66, 5% of dope (20% of dry polymer, 80% of solvent) and 90% of solvent is mixed with the actual dope in a ratio of masterbatch:dope = 1:16 upstream of the spinneret die and then conjointly extruded and precipitated in a coagulation bath consisting of water and solvent. The solvent used is a customary polar aprotic spin dyeing solvent. The fiber thus obtained is spun in a 50:50 blend with regenerated cellulose into a yarn and subsequently processed into a woven or loop-formingly knitted fabric. The result is a textile product having an olive green hue.

20 **Example 2**

An aramid fiber spin dyeing masterbatch consisting of 0.8% of Pigment Blue 15.1, 3.2% of Pigment Red 144, 6% of dope (25% of dry polymer, 75% of solvent) and 90% of solvent is mixed with the actual dope in a ratio of masterbatch:dope = 1:115 upstream of the spinneret die and then conjointly extruded and precipitated in a coagulation bath consisting of water and solvent. The solvent used is a customary polar aprotic spin dyeing solvent.

The fiber thus obtained is spun in a 50:50 blend with regenerated cellulose into a yarn and subsequently processed into a woven or loop-formingly knitted fabric. The result is a textile product having a beige hue.

30

**Example 3**

An aramid fiber spin dyeing masterbatch consisting of 1.4% of Pigment Blue 15.1, 1.4 % of Pigment Red 144 and 2.4% of Pigment Yellow 110, 4.8% of dope (20% of



dry polymer, 80% of solvent) and 90% of solvent is mixed with the actual dope in a ratio of masterbatch:dope = 1:20 upstream of the spinneret die and then conjointly extruded and precipitated in a coagulation bath consisting of water and solvent. The solvent used is a customary polar aprotic spin dyeing solvent.

The fiber thus obtained is spun in a 50:50 blend with regenerated cellulose into a yarn and subsequently processed into a woven or loop-formingly knitted fabric. The result is a textile product having a brown hue.

#### 10 Examples 4 to 8

The textile materials obtained as per Examples 1 to 3 are printed with a camouflage shade in a subsequent step by using print pastes of the following composition:

##### Example 4:

- 15 6.5 g/kg of C.I. Vat Yellow 46
- 15 g/kg of C.I. Vat Yellow 4
- 24 g/kg of C.I. Vat Blue 66
- 700 g/kg of thickening for 2-step fixation
- 254.5 g/kg balance (water or thickening)

20 1,000.00 g

A customary 2-step fixation for vat dyes provides a dark green hue having a reflectance profile which is similar to that of chlorophyll.

##### Example 5:

- 25 6.0 g/kg of C.I. Vat Yellow 46
- 2.5 g/kg of C.I. Vat Yellow 4
- 1.8 g/kg of C.I. Vat Blue 66
- 700 g/kg of thickening for 2-step fixation
- 289.7 g/kg balance (water or thickening)

30 1,000.00 g

A customary 2-step fixation for vat dyes provides a light green hue having a reflectance profile which is similar to that of chlorophyll.

**Example 6:**

40.0 g/kg of C.I. Vat Brown 57

700 g/kg of thickening for 2-step fixation

5 260.0 g/kg balance (water or thickening)

1,000.00 g

A customary 2-step fixation for vat dyes provides a brown hue having a reflectance profile which is similar to that of chlorophyll.

10 **Example 7:**

120.0 g/kg of C.I. Sulphur Black 6

700 g/kg of thickening for 2-step fixation

180.0 g/kg balance (water or thickening)

1,000.00 g

15 A customary 2-step fixation for vat dyes provides a black hue having a reflectance profile which is similar to that of chlorophyll.

**Example 8**

20.0 g/kg of C.I. Vat Yellow 04

20 1.9 g/kg of C.I. Vat Orange 07

6.1 g/kg of C.I. Vat Blue 66

700.0 g/kg of thickening for 2-step fixation

272.0 g/kg balance (water or thickening)

1,000.00 g

25 A customary 2-step fixation for vat dyes provides a light green hue having IR reflectance values which are very close to those of natural chlorophyll.

**Example 9**

The textile materials obtained as per Examples 1 to 3 are cross-dyed in a

30 subsequent step with a mixture of the following vat dyes in a continuous dyeing operation:

5.9 g/l of C.I. Vat Orange 01

7.9 g/l of C.I. Vat Blue 66

3.8 g/l of C.I. Vat Olive 27

What is claimed is:

1. Textile fiber material comprising spun-dyed aramid fibers or mixtures of spun-dyed aramid fibers and undyed cellulosic fibers for producing military camouflage articles, wherein the aramid fiber fraction is spun-dyed with a colorant having a chlorophyll-like reflectance in the IR region.
2. The textile fiber material of claim 1, wherein the aramid fiber fraction is spun-dyed with C.I. Vat Blue 05, C.I. Vat Blue 64, C.I. Vat Blue 66, C.I. Pigment Blue 15, C.I. Pigment Blue 15.1, C.I. Pigment Blue 15.3, C.I. Pigment Blue 28, C.I. Pigment Green 7, C.I. Pigment Green 17, C.I. Pigment Green 36, C.I. Pigment Green 50, C.I. Pigment Black 7, C.I. Pigment Black 11, C.I. Pigment Black 32, C.I. Pigment Yellow 42, C.I. Pigment Yellow 53, C.I. Pigment Yellow 83, C.I. Pigment Yellow 110, C.I. Pigment Yellow 138, C.I. Pigment Yellow 139, C.I. Pigment Yellow 164, C.I. Pigment Yellow 183, C.I. Pigment Yellow 184, C.I. Pigment Brown 24, C.I. Pigment Brown 29, C.I. Pigment Brown 31, C.I. Pigment White 6, C.I. Pigment Red 101, C.I. Pigment Red 144, C.I. Pigment Red 149, C.I. Pigment Red 178, C.I. Pigment Red 179 or the commercial products Sicomix® IR-Schwarz 00-6760, Sicomix® Schwarz 00-8530, Bayferrox Rot 600, Bayferrox Rot 655 or Bayferrox 960.
3. The textile fiber material of claim 1 and/or 2, comprising a mixture of aramid fibers and low-flammable regenerated cellulose fibers.
4. The use of textile fiber material comprising spun-dyed aramid fibers as set forth in claim 1 and/or 2 for producing military camouflage articles, which comprises camouflage patterns being printed on in a conventional manner.
5. The use of textile fiber material comprising mixtures of spun-dyed aramid fibers and undyed cellulosic fibers as set forth in one or more of claims 1 to 3 for producing military camouflage articles, which comprises the cellulose fraction being dyed or camouflage printed.
6. The use of claim 5, wherein an aramid fiber material spun-dyed in medium gray,

green, brown or olive shades is cross-printed with camouflage patterns in black, brown, olive or green shades.

- 5 7. The use of claim 5 and/or 6, wherein the cellulose fraction is dyed or printed with vat or sulfur dyes.
8. The use of claim 7, wherein the vat dyes used are C.I. Vat Yellow 4, C.I. Vat Yellow 33, C.I. Vat Yellow 46, C.I. Vat Orange 1, C.I. Vat Orange 7, C.I. Vat Orange 10 11, C.I. Vat Orange 15, C.I. Vat Blue 5, C.I. Vat Blue 19, C.I. Vat Blue 66, C.I. Vat Green 1, C.I. Vat Green 3, C.I. Vat Green 9, C.I. Vat Green 13, C.I. Vat Brown 1, C.I. Vat Brown 3, C.I. Vat Brown 57, C.I. Vat Black 7, C.I. Vat Black 8, C.I. Vat Black 9, C.I. Vat Black 19, C.I. Vat Black 25, C.I. Vat Black 27 or C.I. Vat Olive 27.
- 15 9. The use of claim 7, wherein the sulfur dyes used are C.I. Sulfur Black 1, C.I. Sulfur Black 6 or C.I. Sulfur Black 7.

**THIS PAGE BLANK (USPTO)**

## INTERNATIONAL SEARCH REPORT

PCT/EP 03/09097

A. CLASSIFICATION OF SUBJECT MATTER  
 IPC 7 D06P3/00 D06P1/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
 IPC 7 D06P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 607 483 A (BURKINSHAW STEPHEN M ET AL) 4 March 1997 (1997-03-04)	1,4
A	column 2, line 5 -column 4, line 56; example 21	6
A	US 5 275 627 A (CATES BARBARA J ET AL) 4 January 1994 (1994-01-04) the whole document	1,4,6
A	US 4 981 488 A (CATES BARBARA J ET AL) 1 January 1991 (1991-01-01) column 3, line 5-57	1,3-7
A	US 4 095 940 A (WEINGARTEN RUDOLF) 20 June 1978 (1978-06-20) the whole document	1
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

16 December 2003

Date of mailing of the international search report

22/12/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3016

Authorized officer

V Beurden-Hopkins, S

# INTERNATIONAL SEARCH REPORT

PCT/EP 03/09097

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EP 1 111 124 A (DYSTAR TEXTILFARBEN GMBH &amp; CO) 27 June 2001 (2001-06-27)  cited in the application  the whole document</p> <p>-----</p>	1



## INTERNATIONAL SEARCH REPORT

PCT/03/09097

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5607483	A	04-03-1997	AT 186580 T 15-11-1999
			AU 700845 B2 14-01-1999
			AU 3083695 A 04-03-1996
			CA 2194456 A1 15-02-1996
			CN 1158646 A 03-09-1997
			DE 69513290 D1 16-12-1999
			DE 69513290 T2 17-02-2000
			DK 772709 T3 25-04-2000
			EP 0772709 A1 14-05-1997
			ES 2138229 T3 01-01-2000
			WO 9604420 A1 15-02-1996
			GB 2305443 A , B 09-04-1997
			GR 3032426 T3 31-05-2000
			JP 10503558 T 31-03-1998
			NZ 290181 A 27-04-1998
			US 5873914 A 23-02-1999
US 5275627	A	04-01-1994	CA 2060373 A1 31-07-1993
			US 4981488 A 01-01-1991
			AU 640949 B2 09-09-1993
			AU 6174190 A 03-04-1991
			EP 0487568 A1 03-06-1992
			JP 4507438 T 24-12-1992
			WO 9102837 A1 07-03-1991
US 4981488	A	01-01-1991	CA 2060373 A1 31-07-1993
			AU 640949 B2 09-09-1993
			AU 6174190 A 03-04-1991
			EP 0487568 A1 03-06-1992
			JP 4507438 T 24-12-1992
			WO 9102837 A1 07-03-1991
			US 5275627 A 04-01-1994
US 4095940	A	20-06-1978	DE 2200323 C1 15-06-1978
			BE 793350 A1
			FR 2370821 A1 09-06-1978
			GB 1501370 A 15-02-1978
			NL 7300160 A 30-12-1977
EP 1111124	A	27-06-2001	DE 19962916 A1 05-07-2001
			CN 1306121 A 01-08-2001
			EP 1111124 A1 27-06-2001
			TR 200003786 A2 23-07-2001
			TW 496918 B 01-08-2002
			US 2001004780 A1 28-06-2001
			ZA 200007771 A 16-07-2001

**THIS PAGE BLANK (USPTO)**